

Aclo Accutech Polypropylene Copolymer CP0436C30L1 Calcium Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Calcium Carbonate (CaCO3) Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0436C30L1-Calcium-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	MD; ASTM D955
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	62	62	ASTM D785
Tensile Strength at Break	15.0 MPa	2180 psi	ASTM D638
Tensile Strength, Yield	19.0 MPa	2760 psi	ASTM D638
Elongation at Break	60 %	60 %	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Tensile Modulus	1.60 GPa	232 ksi	ASTM D638
Flexural Strength	25.0 MPa	3630 psi	ASTM D790
Flexural Modulus	1.300 GPa	188.5 ksi	ASTM D790
Izod Impact, Notched	1.44 J/cm	2.70 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	52.2 °C	126 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	91.1 °C	196 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China