

Aclo Accutech Polypropylene Copolymer CP0436W10L Wollastonite Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0436W10L-Wollastonite-Reinforced.php

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.011 cm/cm	0.011 in/in	MD; ASTM D955
Melt Flow	12 g/10 min	12 g/10 min	ASTM D1238
Ash	10 %	10 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	58	58	ASTM D785
Tensile Strength at Break	15.0 MPa	2180 psi	ASTM D638
Tensile Strength, Yield	22.0 MPa	3190 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Elongation at Yield	6.0 %	6.0 %	ASTM D638
Tensile Modulus	1.250 GPa	181.3 ksi	ASTM D638
Flexural Strength	24.0 MPa	3480 psi	ASTM D790
Flexural Modulus	1.100 GPa	159.5 ksi	ASTM D790
Izod Impact, Notched	1.17 J/cm	2.20 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	93.9 °C	201 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	51.1 °C	124 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China