

Aclo Accutech Polypropylene Copolymer CP0437M10CL Mica Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Mica Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0437M10CL-Mica-Reinforced-Coupled.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	MD; ASTM D955
Melt Flow	19 g/10 min	19 g/10 min	ASTM D1238
Ash	10 %	10 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	53	53	ASTM D785
Tensile Strength at Break	14.0 MPa	2030 psi	ASTM D638
Tensile Strength, Yield	17.0 MPa	2470 psi	ASTM D638
Elongation at Break	17 %	17 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Tensile Modulus	1.20 GPa	174 ksi	ASTM D638
Flexural Strength	21.0 MPa	3050 psi	ASTM D790
Flexural Modulus	1.20 GPa	174 ksi	ASTM D790
Izod Impact, Notched	2.51 J/cm	4.70 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	87.2 °C	189 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	51.1 °C	124 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China