

Aclo Accutech Polypropylene Copolymer CP0437W40L1 Wollastonite Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0437W40L1-Wollastonite-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	MD; ASTM D955
Melt Flow	18 g/10 min	18 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	43	43	ASTM D785
Tensile Strength at Break	14.0 MPa	2030 psi	ASTM D638
Tensile Strength, Yield	17.0 MPa	2470 psi	ASTM D638
Elongation at Break	13 %	13 %	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Tensile Modulus	2.40 GPa	348 ksi	ASTM D638
Flexural Strength	20.0 MPa	2900 psi	ASTM D790
Flexural Modulus	2.299 GPa	333.5 ksi	ASTM D790
Izod Impact, Notched	1.66 J/cm	3.10 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	102 °C	216 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	61.1 °C	142 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China