

Aclo Accutech Polypropylene Homopolymer HP0334T30L Talc Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0334T30L-Talc-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	MD; ASTM D955
Melt Flow	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	84	84	ASTM D785
Tensile Strength at Break	26.0 MPa	3770 psi	ASTM D638
Tensile Strength, Yield	33.0 MPa	4790 psi	ASTM D638
Elongation at Break	15 %	15 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Tensile Modulus	1.900 GPa	275.5 ksi	ASTM D638
Flexural Strength	45.0 MPa	6530 psi	ASTM D790
Flexural Modulus	2.899 GPa	420.5 ksi	ASTM D790
Izod Impact, Notched	0.299 J/cm	0.560 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	120 °C	248 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	67.2 °C	153 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China