

Aclo Accutech Polypropylene Homopolymer HP0334W40L1 Wollastonite Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0334W40L1-Wollastonite-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	MD; ASTM D955
Melt Flow	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	66	66	ASTM D785
Tensile Strength at Break	23.0 MPa	3340 psi	ASTM D638
Tensile Strength, Yield	30.0 MPa	4350 psi	ASTM D638
Elongation at Break	15 %	15 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	3.40 GPa	493 ksi	ASTM D638
Flexural Strength	36.0 MPa	5220 psi	ASTM D790
Flexural Modulus	3.40 GPa	493 ksi	ASTM D790
Izod Impact, Notched	0.411 J/cm	0.770 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	125 °C	257 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China