

Aclo Accutech Polypropylene Homopolymer HP0336C20L1 Calcium Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Calcium Carbonate (CaCO3) Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336C20L1-Calcium-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.013 cm/cm	0.013 in/in	MD; ASTM D955
Melt Flow	12 g/10 min	12 g/10 min	ASTM D1238
Ash	19.7 %	19.7 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	88	88	ASTM D785
Tensile Strength at Break	15.0 MPa	2180 psi	ASTM D638
Tensile Strength, Yield	31.0 MPa	4500 psi	ASTM D638
Elongation at Break	70 %	70 %	ASTM D638
Elongation at Yield	7.0 %	7.0 %	ASTM D638
Tensile Modulus	1.500 GPa	217.5 ksi	ASTM D638
Flexural Strength	36.0 MPa	5220 psi	ASTM D790
Flexural Modulus	1.700 GPa	246.5 ksi	ASTM D790
Izod Impact, Notched	0.422 J/cm	0.790 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	100 °C	212 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	58.9 °C	138 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China