

Aclo Accutech Polypropylene Homopolymer HP0336M20CL Mica Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Mica Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336M20CL-Mica-Reinforced-Coupled.php

Physical Properties	Metric	English	Comments
Density	1.02 g/cc	0.0368 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	MD; ASTM D955
Melt Flow	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Ash	20 %	20 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	74	74	ASTM D785
Tensile Strength at Break	30.0 MPa	4350 psi	ASTM D638
Tensile Strength, Yield	35.0 MPa	5080 psi	ASTM D638
Elongation at Break	15 %	15 %	ASTM D638
Elongation at Yield	6.0 %	6.0 %	ASTM D638
Tensile Modulus	2.40 GPa	348 ksi	ASTM D638
Flexural Strength	46.0 MPa	6670 psi	ASTM D790
Flexural Modulus	2.60 GPa	377 ksi	ASTM D790
Izod Impact, Notched	0.422 J/cm	0.790 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	123 °C	253 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	68.9 °C	156 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China