

Aclo Accutech Polypropylene Homopolymer HP0336M40CL Mica Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Mica Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336M40CL-Mica-Reinforced-Coupled.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	MD; ASTM D955
Melt Flow	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	50	50	ASTM D785
Tensile Strength at Break	31.0 MPa	4500 psi	ASTM D638
Tensile Strength, Yield	33.0 MPa	4790 psi	ASTM D638
Elongation at Break	5.0 %	5.0 %	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Tensile Modulus	3.60 GPa	522 ksi	ASTM D638
Flexural Strength	47.0 MPa	6820 psi	ASTM D790
Flexural Modulus	5.899 GPa	855.6 ksi	ASTM D790
Izod Impact, Notched	0.299 J/cm	0.560 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	130 °C	266 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China