

Aclo Accutech Polypropylene Homopolymer HP0336W30L Wollastonite Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0336W30L-Wollastonite-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.146 g/cc	0.04140 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	MD; ASTM D955
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	86	86	ASTM D785
Tensile Strength at Break	30.0 MPa	4350 psi	ASTM D638
Tensile Strength, Yield	32.0 MPa	4640 psi	ASTM D638
Elongation at Break	14 %	14 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Tensile Modulus	2.899 GPa	420.5 ksi	ASTM D638
Flexural Strength	42.0 MPa	6090 psi	ASTM D790
Flexural Modulus	3.00 GPa	435 ksi	ASTM D790
Izod Impact, Notched	0.352 J/cm	0.660 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	122 °C	252 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	72.8 °C	163 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China