

Aclo Accutech Polypropylene Homopolymer HP0339G25M5CL Glass/Mineral Reinforced Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass/Mineral Reinforced

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Homopolymer-HP0339G25M5CL-GlassMineral-Reinforced-Coupled.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	MD; ASTM D955
Melt Flow	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	98	98	ASTM D785
Tensile Strength at Break	60.0 MPa	8700 psi	ASTM D638
Tensile Strength, Yield	59.0 MPa	8560 psi	ASTM D638
Elongation at Break	6.0 %	6.0 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	3.699 GPa	536.5 ksi	ASTM D638
Flexural Strength	89.01 MPa	12910 psi	ASTM D790
Flexural Modulus	4.799 GPa	696.1 ksi	ASTM D790
Izod Impact, Notched	0.502 J/cm	0.940 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	155 °C	311 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	58.3 °C	137 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China