

Addiplast Addinyl A2 W Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

High molding rateInformation provided by Addiplast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Addiplast-Addinyl-A2-W-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ISO 1183/A

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	79	79	Conditioned; ISO 868
	85	85	ISO 868
Tensile Strength, Yield	60.0 MPa	8700 psi	Conditioned; ISO R 527
	90.0 MPa	13100 psi	ISO R 527
Elongation at Yield	35 %	35 %	ISO R 527
	>= 50 %	>= 50 %	Conditioned; ISO R 527
Modulus of Elasticity	1.30 GPa	189 ksi	Conditioned; ISO 178
	3.05 GPa	442 ksi	ISO 178
Izod Impact, Notched (ISO)	6.00 kJ/m ²	2.86 ft-lb/in ²	ISO 180/1A
	12.0 kJ/m ²	5.71 ft-lb/in ²	Conditioned; ISO 180/1A
Charpy Impact Unnotched	NB	NB	ISO 179/IeU
	NB	NB	Conditioned; ISO 179/IeU
Charpy Impact, Notched	0.450 J/cm ²	2.14 ft-lb/in ²	ISO 179/IeA
	1.10 J/cm ²	5.23 ft-lb/in ²	Conditioned; ISO 179/IeA

Thermal Properties	Metric	English	Comments
CTE, linear	70.0 µm/m-°C	38.9 µin/in-°F	ASTM E831
Melting Point	260 °C	500 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	90.0 °C	194 °F	ISO 75-2/AF

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	Conditioned; CEI 60093
	1.00e+15 ohm-cm	1.00e+15 ohm-cm	CEI 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	Conditioned; CEI 60093
	1.00e+15 ohm	1.00e+15 ohm	CEI 60093
Dielectric Strength	27.0 kV/mm	686 kV/in	Conditioned; CEI 60243-1
	28.0 kV/mm	711 kV/in	CEI 60243-1
Comparative Tracking Index	600 V	600 V	CEI 60112/Solution A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China