

Addiplast Addinyl C2 ZV40 Nylon 66/6, 40% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6/66 , Nylon 66/6, 40% Glass Fiber Reinforced

Material Notes:

Glass fiber reinforced, increased thermal aging stabilityInformation provided by Addiplast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Addiplast-Addinyl-C2-ZV40-Nylon-666-40-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.46 g/cc	0.0527 lb/in ³	ISO 1183/A

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	79	79	Conditioned; ISO 868
	85	85	ISO 868
Tensile Strength at Break	130 MPa	18900 psi	Conditioned; ISO R 527
	195 MPa	28300 psi	ISO R 527
Elongation at Yield	3.0 %	3.0 %	ISO R 527
	6.0 %	6.0 %	Conditioned; ISO R 527
Modulus of Elasticity	6.10 GPa	885 ksi	Conditioned; ISO 178
	11.5 GPa	1670 ksi	ISO 178
Izod Impact, Notched (ISO)	16.0 kJ/m ²	7.61 ft-lb/in ²	ISO 180/1A
	22.0 kJ/m ²	10.5 ft-lb/in ²	Conditioned; ISO 180/1A
Charpy Impact Unnotched	6.50 J/cm ²	30.9 ft-lb/in ²	ISO 179/IeU
	7.50 J/cm ²	35.7 ft-lb/in ²	Conditioned; ISO 179/IeU
Charpy Impact, Notched	1.10 J/cm ²	5.23 ft-lb/in ²	ISO 179/IeA
	1.80 J/cm ²	8.57 ft-lb/in ²	Conditioned; ISO 179/IeA

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 µm/m-°C	16.7 µin/in-°F	ASTM E831
Melting Point	243 °C	469 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	235 °C	455 °F	ISO 75-2/AF

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	Conditioned; CEI 60093
	1.00e+15 ohm-cm	1.00e+15 ohm-cm	CEI 60093
Dielectric Strength	30.0 kV/mm	762 kV/in	Conditioned; CEI 60243-1
	35.0 kV/mm	889 kV/in	CEI 60243-1
Comparative Tracking Index	550 V	550 V	CEI 60112/Solution A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China