

Addiplast Addinyl PMD 20170 Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

Galvanizing Information provided by Addiplast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Addiplast-Addinyl-PMD-20170-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.46 g/cc	0.0527 lb/in ³	ISO 1183/A

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	84	84	Conditioned; ISO 868
	88	88	ISO 868
Tensile Strength at Break	60.0 MPa	8700 psi	Conditioned; ISO R 527
	85.0 MPa	12300 psi	ISO R 527
Elongation at Yield	5.0 %	5.0 %	ISO R 527
	25 %	25 %	Conditioned; ISO R 527
Modulus of Elasticity	1.60 GPa	232 ksi	Conditioned; ISO 178
	5.00 GPa	725 ksi	ISO 178
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	ISO 180/1A
	9.00 kJ/m ²	4.28 ft-lb/in ²	Conditioned; ISO 180/1A
Charpy Impact Unnotched	3.00 J/cm ²	14.3 ft-lb/in ²	ISO 179/IeU
	NB	NB	Conditioned; ISO 179/IeU
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	ISO 179/IeA
	0.900 J/cm ²	4.28 ft-lb/in ²	Conditioned; ISO 179/IeA

Thermal Properties	Metric	English	Comments
CTE, linear	55.0 µm/m-°C	30.6 µin/in-°F	ASTM E831
Melting Point	260 °C	500 °F	ISO 3146/C2
Deflection Temperature at 1.8 MPa (264 psi)	140 °C	284 °F	ISO 75-2/AF

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	Conditioned; CEI 60093
	1.00e+15 ohm-cm	1.00e+15 ohm-cm	CEI 60093
Comparative Tracking Index	550 V	550 V	CEI 60112/Solution A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China