

Adell AR-17 Nylon 66, 35% Glass Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Glass Fiber Filled

Material Notes:

Data provided by Adell Plastics, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Adell-AR-17-Nylon-66-35-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in ³	ASTM D792
Water Absorption	0.80 %	0.80 %	24 hour immersion; ASTM D570
Linear Mold Shrinkage	0.0035 cm/cm	0.0035 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	98	98	ASTM D785
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength, Ultimate	186 MPa	27000 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	265 MPa	38400 psi	ASTM D790
Flexural Modulus	9.00 GPa	1310 ksi	ASTM D790
Compressive Yield Strength	245 MPa	35500 psi	ASTM D695
Izod Impact, Notched	1.10 J/cm	2.06 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	263 °C	505 °F	ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	>= 249 °C	>= 480 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	249 °C	480 °F	ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China