

Adell AR-34 Nylon 66, 20% Glass Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled

Material Notes:

Data provided by Adell Plastics, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Adell-AR-34-Nylon-66-20-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.29 g/cc	0.0466 lb/in ³	ASTM D792
Water Absorption	0.90 %	0.90 %	24 hour immersion; ASTM D570
Linear Mold Shrinkage	0.0045 cm/cm	0.0045 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	96	96	ASTM D785
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Ultimate	124 MPa	18000 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	214 MPa	31000 psi	ASTM D790
Flexural Modulus	7.60 GPa	1100 ksi	ASTM D790
Compressive Yield Strength	207 MPa	30000 psi	ASTM D695
Izod Impact, Notched	0.800 J/cm	1.50 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	263 °C	505 °F	ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	>= 249 °C	>= 480 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	246 °C	475 °F	ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China