

Akzo Nobel Trigonox® C-C75 Polymerization Initiator

Category : Other Engineering Material , Catalyst/Initiator , Polymer

Material Notes:

Initiator for the (co)polymerization of ethylene, styrene, acrylonitrile, acrylates and methacrylates. Chemical Description: tert-Butyl peroxybenzoate, 75% solution in odorless mineral spirits CAS Number: 614-45-9 Acronym: TBPB; Tx C Information provided by Akzo Nobel Polymer Chemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Akzo-Nobel-Trigonox-C-C75-Polymerization-Initiator.php

Physical Properties	Metric	English	Comments
One Hour Half Life Temperature	122 °C	252 °F	
Storage Temperature	0.000 - 25.0 °C	32.0 - 77.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China