

Alcoa KAMA 3300 Very High Impact Polystyrene (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS)

Material Notes:

CapabilitiesGauge: .007" to .060" (178 to 1524µm)Width: 12" to 62" (304 to 1575mm)Core Size: 6" standard cores, 3" and 8" availableRoll O.D.: 29" standard, up to 40" availableSilicone coating availableCorona treatment availableCustom colors availableMedical grade available5 strategic manufacturing locationsPropertiesVery high impact propertiesUsed for deeper draw and hinged applicationsForms easilyFDA compliant materialKosher materialInformation provided by Alcoa Kama Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Alcoa-KAMA-3300-Very-High-Impact-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	
Thickness	178 - 1520 microns	7.00 - 60.0 mil	
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	13.8 - 29.0 MPa	2000 - 4200 psi	ASTM D638
Elongation at Break	40 - 100 %	40 - 100 %	ASTM D638
Flexural Modulus	1.38 - 2.41 GPa	200 - 350 ksi	ASTM D790
Izod Impact, Notched	1.33 - 1.82 J/cm	2.50 - 3.40 ft-lb/in	ASTM D265

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	73.9 °C	165 °F	
Minimum Service Temperature, Air	-28.9 °C	-20.0 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	127 - 166 °C	260 - 330 °F	Thermoforming Temp

Descriptive Properties	Value	Comments
Resistance to Acid	Good to Excellent	
Resistance to Alcohols	Good to Excellent	
Resistance to Alkalis	Excellent	
Resistance to Fat, Grease, and Oil	Good	

Resistance to Hydrocarbon Solvents Descriptive Properties	Poor Value	Comments
Resistance to Strong Oxidizers	Poor	
Yield, in ² /lb/mil	26360	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China