

Alcoa Toolrite 2011®-T3 Aluminum

Category : Metal , Nonferrous Metal , Aluminum Alloy , 2000 Series Aluminum Alloy

Material Notes:

Weldability = D; Stress Corrosion Cracking Resistance = D; General Corrosion Resistance = D (A = best; E = worst). General 2011 characteristics and uses: Good machinability, especially free-cutting qualities, good mechanical properties. Excellent surface finish capability. The T451 temper offers good deep drilling characteristics. Uses: Adapters, carburetor parts, clock parts and gears, knobs, camera parts, meter shafts and gears, nozzles, pencil and pen parts, oil line filters, pipe stems and filters, radio parts, screwdriver caps, spindles, telephone parts, TV fittings, tripod fittings, machine parts, hose parts, pipe stems. Data supplied by the manufacturer, Alcoa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Alcoa-Toolrite-2011-T3-Aluminum.php

Physical Properties	Metric	English	Comments
Density	2.82 g/cc	0.102 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	95	95	500 kg load/10 mm ball
Hardness, Knoop	120	120	Estimated from Brinell
Hardness, Rockwell A	39.5	39.5	Estimated from Brinell
Hardness, Rockwell B	60	60	Estimated from Brinell
Hardness, Vickers	107	107	Estimated from Brinell
Tensile Strength, Ultimate	>= 310 MPa	>= 45000 psi	
Tensile Strength, Yield	>= 262 MPa	>= 38000 psi	Larger sizes may be lower.
Elongation at Break	10 %	10 %	
Modulus of Elasticity	70.0 GPa	10200 ksi	
Fatigue Strength	124 MPa @# of Cycles 5.00e+8	18000 psi @# of Cycles 5.00e+8	completely reversed; R. R. Moore Machine and specimen.
Machinability	90 %	90 %	0-100 Scale (A=90; B=70; C=50; D=30; E=10)
Shear Strength	221 MPa	32100 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	22.9 µm/m-°C @Temperature 20.0 - 100 °C	12.7 µin/in-°F @Temperature 68.0 - 212 °F	average

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Component Elements Properties	Metric	English	Comments
Aluminum, Al	93.7 %	93.7 %	
Bismuth, Bi	0.20 - 0.60 %	0.20 - 0.60 %	
Copper, Cu	5.0 - 6.0 %	5.0 - 6.0 %	
Iron, Fe	<= 0.70 %	<= 0.70 %	
Lead, Pb	0.20 - 0.60 %	0.20 - 0.60 %	
Silicon, Si	<= 0.40 %	<= 0.40 %	
Zinc, Zn	<= 0.30 %	<= 0.30 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000440 ohm-cm	0.00000440 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China