

Alliance BIN-72 Bonded (Composite) Magnetic Material

Category : Ceramic , Metal , Electronic/Magnetic Alloy

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Alliance-BIN-72-Bonded-Composite-Magnetic-Material.php

Physical Properties	Metric	English	Comments
Density	4.50 - 5.50 g/cc	0.163 - 0.199 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	25.0 - 40.0 MPa	3630 - 5800 psi	
Flexural Strength	60.0 - 80.0 MPa	8700 - 11600 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	60.0 - 80.0 $\mu\text{m/m-}^{\circ}\text{C}$	33.3 - 44.4 $\mu\text{in/in-}^{\circ}\text{F}$	Parallel DOM
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Maximum Service Temperature, Air	100 $^{\circ}\text{C}$	212 $^{\circ}\text{F}$	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00400 - 0.00700 ohm-cm	0.00400 - 0.00700 ohm-cm	
Magnetic Coercive Force, Hc	5250 Oe	5250 Oe	
	8980 Oe	8980 Oe	Intrinsic
Magnetic Remanence, Br	6700 Gauss	6700 Gauss	
Magnetic Maximum Energy Product, BH	9.1 MGOe	9.1 MGOe	
Curie Temperature	300 - 470 $^{\circ}\text{C}$	572 - 878 $^{\circ}\text{F}$	

Descriptive Properties	Value	Comments
Reversible Temp Coef., Bd	-0.105 %/ $^{\circ}\text{C}$	
Reversible Temp Coef., Hd	-0.40 %/ $^{\circ}\text{C}$	
Temperature Coefficient, Br	-0.1 %/ $^{\circ}\text{C}$	(20-100 $^{\circ}\text{C}$)
Temperature Coefficient, Hci	-0.4 %/ $^{\circ}\text{C}$	(20-100 $^{\circ}\text{C}$)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China