

## Alliance N-30UH Neodymium Iron Boron Magnetic Material

Category : Metal , Electronic/Magnetic Alloy , Ferrous Metal , Ferritic

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Alliance-N-30UH-Neodymium-Iron-Boron-Magnetic-Material.php](http://www.lookpolymers.com/polymer_Alliance-N-30UH-Neodymium-Iron-Boron-Magnetic-Material.php)

| Physical Properties | Metric           | English                          | Comments |
|---------------------|------------------|----------------------------------|----------|
| Density             | 7.50 - 7.80 g/cc | 0.271 - 0.282 lb/in <sup>3</sup> |          |

| Mechanical Properties      | Metric         | English             | Comments |
|----------------------------|----------------|---------------------|----------|
| Hardness, Vickers          | 570 - 580      | 570 - 580           |          |
| Tensile Strength, Ultimate | 80.0 MPa       | 11600 psi           |          |
| Modulus of Elasticity      | 150 - 160 GPa  | 21800 - 23200 ksi   |          |
| Flexural Strength          | 180 - 270 MPa  | 26100 - 39200 psi   |          |
| Compressive Strength       | 850 - 1050 MPa | 123000 - 152000 psi |          |

| Thermal Properties               | Metric                                 | English                                             | Comments     |
|----------------------------------|----------------------------------------|-----------------------------------------------------|--------------|
| CTE, linear                      | 5.00 $\mu\text{m/m-}^{\circ}\text{C}$  | 2.78 $\mu\text{in/in-}^{\circ}\text{F}$             | Parallel DOM |
|                                  | @Temperature 20.0 $^{\circ}\text{C}$   | @Temperature 68.0 $^{\circ}\text{F}$                |              |
| CTE, linear, Transverse to Flow  | -1.00 $\mu\text{m/m-}^{\circ}\text{C}$ | -0.556 $\mu\text{in/in-}^{\circ}\text{F}$           |              |
|                                  | @Temperature 23.0 $^{\circ}\text{C}$   | @Temperature 73.4 $^{\circ}\text{F}$                |              |
| Specific Heat Capacity           | 0.440 J/g- $^{\circ}\text{C}$          | 0.105 BTU/lb- $^{\circ}\text{F}$                    |              |
| Thermal Conductivity             | 9.00 W/m-K                             | 62.5 BTU-in/hr-ft <sup>2</sup> - $^{\circ}\text{F}$ |              |
| Maximum Service Temperature, Air | 180 $^{\circ}\text{C}$                 | 356 $^{\circ}\text{F}$                              |              |

| Electrical Properties               | Metric                     | English                    | Comments  |
|-------------------------------------|----------------------------|----------------------------|-----------|
| Electrical Resistivity              | 0.000120 - 0.000160 ohm-cm | 0.000120 - 0.000160 ohm-cm |           |
| Magnetic Coercive Force, Hc         | 10200 Oe                   | 10200 Oe                   | Intrinsic |
|                                     | 25000 Oe                   | 25000 Oe                   |           |
| Magnetic Remanence, Br              | 11000 Gauss                | 11000 Gauss                |           |
| Magnetic Maximum Energy Product, BH | 28 - 31 MGOe               | 28 - 31 MGOe               |           |

| Electrical Properties        | Metric | English    | Comments   |
|------------------------------|--------|------------|------------|
| Descriptive Properties       |        | Value      | Comments   |
| Reversible Temp Coef., Bd    |        | -0.11 %/°C |            |
| Reversible Temp Coef., Hd    |        | -0.51 %/°C |            |
| Temperature Coefficient, Br  |        | -0.11 %/°C | (20-100°C) |
| Temperature Coefficient, Hci |        | -0.72 %/°C | (20-100°C) |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China