

Alliance Polymers Zythane™ 4045D Thermoplastic Polyurethane Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane TPE

Material Notes:

Zythane™ 4045D is a polycaprolactone-based TPU specifically formulated for injection molding applications .It exhibits excellent low compression set, abrasion resistance and toughness and has good hydrolytic stability, oil, fuel and solvent resistance. It is supplied uncolored in pellet form. Availability: North AmericaFeatures: Fuel Resistant, Good Toughness, Oil Resistant, Hydrolytically Stable, Solvent Resistant, Good Abrasion Resistance Appearance: ColorlessForms: PelletsProcessing Method: Injection MoldingInformation provided by Alliance Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Alliance-Polymers-Zythane-4045D-Thermoplastic-Polyurethane-Elastomer.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	95	95	ASTM D2240
Hardness, Shore D	45	45	ASTM D2240
Tensile Strength at Break	50.0 MPa	7250 psi	ASTM D412
Tensile Stress	9.03 MPa	1310 psi	ASTM D412
	@Strain 100 %	@Strain 100 %	
	21.0 MPa	3050 psi	ASTM D412
	@Strain 300 %	@Strain 300 %	
Elongation at Break	500 %	500 %	ASTM D412
Tear Strength	100 kN/m	571 pli	Die C; ASTM D412
Taber Abrasion, mg/1000 Cycles	40	40	ASTM D1044
Abrasion	45	45	mm³; DIN 53516
Compression Set	23 %	23 %	ASTM D3995B
	@Temperature 22.8 °C, Time 79200 sec	@Temperature 73.0 °F, Time 22.0 hour	
	43 %	43 %	ASTM D3995B
	@Temperature 70.0 °C, Time 259000 sec	@Temperature 158 °F, Time 72.0 hour	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Vicat Softening Point Thermal Properties	147 °C Metric	297 °F English	ASTM D1525 Comments
Brittleness Temperature	-22.0 °C	-7.60 °F	ASTM D746
Flammability, UL94	HB	HB	
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Processing Properties	Metric	English	Comments
Processing Temperature	205 - 215 °C	401 - 419 °F	Injection
Rear Barrel Temperature	190 °C	374 °F	Injection
Middle Barrel Temperature	200 °C	392 °F	Injection
Front Barrel Temperature	210 °C	410 °F	Injection
Nozzle Temperature	205 - 215 °C	401 - 419 °F	Injection
Mold Temperature	25.0 - 60.0 °C	77.0 - 140 °F	Injection
Injection Velocity	>= 10.0 mm/sec	>= 0.394 in/sec	Injection
Drying Temperature	85.0 °C	185 °F	Injection
Dry Time	4.00 hour	4.00 hour	Injection
Back Pressure	0.600 - 1.20 MPa	87.0 - 174 psi	Injection
Clamp Pressure	40.0 - 70.3 MPa	5800 - 10200 psi	Injection
Screw Speed	60 - 200 rpm	60 - 200 rpm	Injection

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China