

Alliance Polymers Zythane™ 7050D Thermoplastic Polyurethane Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane TPE

Material Notes:

Zythane™ 7050D is a polycaprolactone-based TPU specifically formulated for injection molding applications .It exhibits excellent low compression set, abrasion resistance and toughness and has good hydrolytic stability, oil, fuel and solvent resistance. It is supplied uncolored in pellet form. Availability: North AmericaFeatures: Fuel Resistant, Good Toughness, Oil Resistant, Hydrolytically Stable, Solvent Resistant, Good Abrasion Resistance Appearance: ColorlessForms: PelletsProcessing Method: Injection Molding and ExtrusionInformation provided by Alliance Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Alliance-Polymers-Zythane-7050D-Thermoplastic-Polyurethane-Elastomer.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in³	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	50	50	ASTM D2240
Tensile Strength at Break	41.0 MPa	5950 psi	ASTM D412
Tensile Stress	14.0 MPa	2030 psi	ASTM D412
	@Strain 100 %	@Strain 100 %	
	27.0 MPa	3920 psi	ASTM D412
	@Strain 300 %	@Strain 300 %	
Elongation at Break	450 %	450 %	ASTM D412
Tear Strength	170 kN/m	971 pli	Die C; ASTM D412
Taber Abrasion, mg/1000 Cycles	50	50	ASTM D1044
Abrasion	23	23	mm³; DIN 53516
Compression Set	33 %	33 %	ASTM D3995B
	@Temperature 22.8 °C, Time 79200 sec	@Temperature 73.0 °F, Time 22.0 hour	
	46 %	46 %	ASTM D3995B
	@Temperature 70.0 °C, Time 259000 sec	@Temperature 158 °F, Time 72.0 hour	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	130 °C	266 °F	ASTM D1525

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Processing Properties	Metric	English	Comments
Processing Temperature	210 °C	410 °F	Gate Temperature; Extrusion
	210 - 220 °C	410 - 428 °F	Injection
Rear Barrel Temperature	195 °C	383 °F	Injection
Middle Barrel Temperature	205 °C	401 °F	Injection
Front Barrel Temperature	215 °C	419 °F	Injection
Nozzle Temperature	210 - 220 °C	410 - 428 °F	Injection
Zone 1	195 °C	383 °F	Extrusion
Zone 2	205 °C	401 °F	Extrusion
Zone 3	215 °C	419 °F	Extrusion
Die Temperature	220 °C	428 °F	Extrusion
Mold Temperature	25.0 - 60.0 °C	77.0 - 140 °F	Injection
Injection Velocity	>= 10.0 mm/sec	>= 0.394 in/sec	Injection
Drying Temperature	90.0 °C	194 °F	Injection
	90.0 °C	194 °F	Extrusion
Dry Time	4.00 hour	4.00 hour	Injection
	4.00 hour	4.00 hour	Extrusion
Back Pressure	0.300 - 1.30 MPa	43.5 - 189 psi	Injection
Clamp Pressure	40.0 - 70.3 MPa	5800 - 10200 psi	Injection
Screw Speed	60 - 200 rpm	60 - 200 rpm	Injection

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China