

Americas Styrenics EA3130 High Heat Crystal Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Heat Resistant Grade

Material Notes:

Product Characteristics Additive Free Food Contact Compliant Typical Applications Medical Parts Color Concentrate Carrier Low Profile Additives Information provided by Americas Styrenics LLC.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Americas-Styrenics-EA3130-High-Heat-Crystal-Polystyrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955
Melt Flow	4.8 g/10 min @Load 5.00 kg, Temperature 200 °C	4.8 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	107	107	ASTM D785
Tensile Strength at Break	49.6 MPa	7200 psi	ASTM D638
Tensile Strength	49.6 MPa	7200 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Tensile Modulus	3.10 GPa	450 ksi	ASTM D638
Flexural Strength	65.5 MPa	9500 psi	ASTM D790
Flexural Modulus	3.24 GPa	470 ksi	ASTM D790
Izod Impact, Notched	0.214 J/cm	0.400 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 µm/m-°C	50.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	97.2 °C	207 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	87.8 °C	190 °F	ASTM D648
Vicat Softening Point	107 °C	224 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China