

Ametek P430L P/M Stainless Steel, Sintered from 6.2 g/cc Green Density

Category : Metal , Ferrous Metal , Stainless Steel , T 400 Series Stainless Steel

Material Notes:

Powder apparent bulk density 2.8 g/cc; powder flow 30 sec/50g. Compacting properties measured on powders with 1% lithium stearite. Sintering was done in dissociated ammonia at 1121°C (2050°F) for 45 minutes. Sintered properties below were determined using transverse rupture bars. Compacting pressure 38 tsi. Green strength 1200 psi. Dimensional change from die size -0.8%. Information provided by Ametek Specialty Metal Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ametek-P430L-PM-Stainless-Steel-Sintered-from-62-gcc-Green-Density.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	340 MPa	49300 psi	
Elongation at Break	1.5 %	1.5 %	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.020 %	0.020 %	
Chromium, Cr	17 %	17 %	
Iron, Fe	82 %	82 %	as balance
Manganese, Mn	0.20 %	0.20 %	
Phosphorous, P	0.010 %	0.010 %	
Silicon, Si	0.90 %	0.90 %	
Sulfur, S	0.020 %	0.020 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China