

Arkema Group Evatane® 1020 VB 3 Ethylene Vinyl Acetate

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate; Molded/Extruded

Material Notes:

EVA copolymer made by high pressure tubular process. Applications Grade for molding rigid articles. Examples: closures, ice trays.ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Evatane-1020-VB-3-Ethylene-Vinyl-Acetate.php

Physical Properties	Metric	English	Comments
Melt Flow	2.63 g/10 min	2.63 g/10 min	
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Modulus	0.130 GPa	18.9 ksi	1 mm/min

Thermal Properties	Metric	English	Comments
Melting Point	104 °C	219 °F	10°C/min
Vicat Softening Point	83.0 °C	181 °F	50°C/hr; 50N

Optical Properties	Metric	English	Comments
Transmission, Visible	80 %	80 %	Mfr. reports 'Transparent' but doesn't quantify.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China