

Arkema Group Evatane® 1350 VN 5 Ethylene Vinyl Acetate

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate; Molded/Extruded

Material Notes:

EVA copolymer made by high pressure tubular process. Applications Grade for molding very flexible articles. Examples: gaskets.ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Evatane-1350-VN-5-Ethylene-Vinyl-Acetate.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	
Melt Flow	44.7 g/10 min @Load 2.16 kg, Temperature 190 °C	44.7 g/10 min @Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	2.50 MPa	363 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	Nominal Strain; 50 mm/min
Tensile Modulus	0.0450 GPa	6.53 ksi	1 mm/min

Thermal Properties	Metric	English	Comments
Melting Point	84.0 °C	183 °F	10°C/min
Vicat Softening Point	53.0 °C	127 °F	50°C/hr; 50N

Optical Properties	Metric	English	Comments
Transmission, Visible	80 %	80 %	Mfr. reports 'Transparent' but doesn't quantify.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China