

Arkema Group KYNAR® 720, 720 HDP Polyvinylidene Fluoride Homopolymer-Injection Molding and Extrusion

Category : Polymer , Thermoplastic , Fluoropolymer , PVDF , Polyvinylidene fluoride (PVDF), Molded/Extruded

Material Notes:

Characteristics: Natural resin - translucent, off-white hemispheres. HDP indicates higher color stability. High stability in harsh thermal, chemical and ultraviolet environments. High toughness and mechanical strength, low permeability, fire resistance, abrasion resistance; low-smoke emission; high purity Applications: Chemical processing – production, storage and transfer of corrosive fluids Electronics – protective sheathing, plenum and wiring insulation Semi-conductor industry Food stuff and Healthcare industries Transportation – fuel line and pipe, thermoformed body components Listed properties are typical for 700 series. Information provided by Arkema Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-KYNAR-720-720-HDP-Polyvinylidene-Fluoride-Homopolymer-Injection-Molding-and-Extrusion.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.77 - 1.79 g/cc	1.77 - 1.79 g/cc	ASTM D792
Bulk Density	0.961 g/cc	0.0347 lb/in ³	
Water Absorption	0.010 - 0.030 % @Time 86400 sec	0.010 - 0.030 % @Time 24.0 hour	Immersion; ASTM D570
Viscosity	400000 - 1.20e+6 cP @Shear Rate 100 1/s, Temperature 232 °C	400000 - 1.20e+6 cP @Shear Rate 100 1/s, Temperature 450 °F	Melt Viscosity; ASTM D3835
Linear Mold Shrinkage, Flow	0.020 - 0.035 cm/cm @Time 86400 sec	0.020 - 0.035 in/in @Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.016 - 0.030 cm/cm @Time 86400 sec	0.016 - 0.030 in/in @Time 24.0 hour	
Melt Flow	5.0 - 29 g/10 min @Load 3.80 kg, Temperature 232 °C	5.0 - 29 g/10 min @Load 8.38 lb, Temperature 450 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	75 - 80	75 - 80	ASTM D2240
Tensile Strength at Break	34.0 - 55.0 MPa	4930 - 7980 psi	ASTM D638
Tensile Strength, Yield	45.0 - 55.0 MPa	6530 - 7980 psi	ASTM D638
Elongation at Break	50 - 200 %	50 - 200 %	ASTM D638
Elongation at Yield	5.0 - 10 %	5.0 - 10 %	ASTM D638

Mechanical Properties	Metric	English	Comments
Tensile Modulus	1.379 - 2.31 GPa	200.0 - 335 ksi	ASTM D638
Flexural Strength	58.0 - 76.0 MPa @Strain 5.00 %	8410 - 11000 psi @Strain 5.00 %	ASTM D790
Flexural Modulus	1.655 - 2.31 GPa	240.0 - 335 ksi	ASTM D790
Compressive Strength	69.0 - 103 MPa	10000 - 14900 psi	ASTM D695
Izod Impact, Notched	1.07 - 2.14 J/cm	2.00 - 4.00 ft-lb/in	ASTM D256
Izod Impact, Unnotched	10.7 - 42.7 J/cm	20.0 - 80.0 ft-lb/in	ASTM D256
Coefficient of Friction, Dynamic	0.14	0.14	vs. steel; ASTM D1894
Coefficient of Friction, Static	0.20	0.20	vs. steel; ASTM D1894
Taber Abrasion, mg/1000 Cycles	5.0 - 9.0	5.0 - 9.0	1000 g pad; CS-17

Thermal Properties	Metric	English	Comments
CTE, linear	119 - 144 $\mu\text{m/m-}^{\circ}\text{C}$	66.0 - 80.0 $\mu\text{in/in-}^{\circ}\text{F}$	ASTM D696
Specific Heat Capacity	1.17 - 1.51 J/g- $^{\circ}\text{C}$	0.280 - 0.360 BTU/lb- $^{\circ}\text{F}$	DSC
Thermal Conductivity	0.170 - 0.190 W/m-K	1.18 - 1.32 BTU-in/hr-ft ² - $^{\circ}\text{F}$	ASTM D433
Melting Point	165 - 172 $^{\circ}\text{C}$	329 - 342 $^{\circ}\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	125 - 140 $^{\circ}\text{C}$	257 - 284 $^{\circ}\text{F}$	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	105 - 115 $^{\circ}\text{C}$	221 - 239 $^{\circ}\text{F}$	ASTM D648
Glass Transition Temp, Tg	-40.0 - -38.0 $^{\circ}\text{C}$ @Frequency 1.00 Hz	-40.0 - -36.4 $^{\circ}\text{F}$ @Frequency 1.00 Hz	DMA
Decomposition Temperature	375 $^{\circ}\text{C}$	707 $^{\circ}\text{F}$	1% wt loss / in air; TGA
	410 $^{\circ}\text{C}$	770 $^{\circ}\text{F}$	1% wt loss / in nitrogen; TGA
Flammability, UL94	V-0	V-0	
Oxygen Index	44 %	44 %	ASTM D2868
	60 %	60 %	select grades; ASTM D2868

Electrical Properties	Metric	English	Comments
	2.00e+14 ohm-cm	2.00e+14 ohm-cm	

Volume Resistivity Electrical Properties	Metric @ Temperature 20.0 °C	English @ Temperature 68.0 °F	65% RH· ASTM D257 Comments
Dielectric Constant	4.5	4.5	ASTM D150
	@Frequency 1.00e+8 Hz	@Frequency 1.00e+8 Hz	
	9.5	9.5	ASTM D150
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	66.9 kV/mm	1700 kV/in	ASTM D149
Dissipation Factor	0.010 - 0.21	0.010 - 0.21	ASTM D150
	@Frequency 100 Hz	@Frequency 100 Hz	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	190 - 210 °C	374 - 410 °F	Injection Molding
	195 - 220 °C	383 - 428 °F	Tube Extrusion
Middle Barrel Temperature	200 - 220 °C	392 - 428 °F	Injection Molding
	210 - 240 °C	410 - 464 °F	Tube Extrusion
Front Barrel Temperature	200 - 240 °C	392 - 464 °F	Injection Molding
	210 - 240 °C	410 - 464 °F	Tube Extrusion
Nozzle Temperature	200 - 240 °C	392 - 464 °F	Injection Molding
Die Temperature	210 - 250 °C	410 - 482 °F	Tube Extrusion
Head Temperature	210 - 240 °C	410 - 464 °F	Tube Extrusion
Mold Temperature	50.0 - 90.0 °C	122 - 194 °F	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China