

Arkema Group ORGASOL® 2001 UD Nat 2 Polyamide 12, Food Contact Approved

Category : Polymer , Thermoplastic , Nylon , Nylon 12

Material Notes:

Information provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-ORGASOL-2001-UD-Nat-2-Polyamide-12-Food-Contact-Approved.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in ³	ISO 1183
Apparent Bulk Density	0.215 g/cc	0.00777 lb/in ³	ISO 1068
Particle Size	4.0 - 6.0 µm	4.0 - 6.0 µm	Average; ATO 40-41-0 (Coulter Counter)
pH	>= 6.0	>= 6.0	ATO 40-40-0 (pH meter)
Specific Surface Area	9.0 m ² /g	9.0 m ² /g	ATO 40-45-0 (BET)

Thermal Properties	Metric	English	Comments
Melting Point	177 °C	351 °F	ISO 3146

Processing Properties	Metric	English	Comments
Moisture Content	1.0 %	1.0 %	ISO 1625

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China