

Arkema Group Orevac® 9305 Film EVA-MAH Terpolymer

Category : Polymer , Film , Thermoplastic , Ethylene Vinyl Acetate

Material Notes:

EVA Terpolymers based Main Application: Hot melt adhesives Information provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Orevac-9305-Film-EVA-MAH-Terpolymer.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in³	ASTM D1505
Vinyl Acetate Content	26 - 30 %	26 - 30 %	
Melt Flow	150 - 210 g/10 min @Load 2.16 kg, Temperature 190 °C	150 - 210 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	67.0 °C	153 °F	D.S.C. method
Vicat Softening Point	<= 40.0 °C	<= 104 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China