

Arkema Group Orgalloy® LE 60LMXV Flexible Nylon Alloy (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon, Flexible Alloy

Material Notes:

LE series, flexible polyamide alloys: processability on PE screw, low moisture absorption, chemical resistance (no known solvents). Suited to the extrusion of tubes (hydraulic, pneumatic, painting...)ISO data provided by the manufacturer, Arkema.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Orgalloy-LE-60LMXV-Flexible-Nylon-Alloy-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Water Absorption	5.5 %	5.5 %	
Moisture Absorption at Equilibrium	1.8 %	1.8 %	Humidity Absorption
Melt Flow	4.0 g/10 min @Load 2.16 kg, Temperature 235 °C	4.0 g/10 min @Load 4.76 lb, Temperature 455 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	30.0 MPa	4350 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	Nominal Strain; 50 mm/min
Elongation at Yield	7.0 %	7.0 %	50 mm/min
Tensile Modulus	0.600 GPa	87.0 ksi	1 mm/min

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	10°C/min
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	
	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China