

Arkema Group Pebax® 2533 SA 01 Polyether Block Amide (PEBA)

Category : Polymer , Thermoplastic , Polyether Block Amide (PEBA)

Material Notes:

Polyether block amide PEBAX® 2533 SA 01 is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This SA grade is specially designed to food uses. Information provided by Arkema Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arkema-Group-Pebax-2533-SA-01-Polyether-Block-Amide-PEBA.php

Physical Properties	Metric	English	Comments
Density	1.00 g/cc	0.0361 lb/in³	ISO 1183
Water Absorption	1.2 % @Temperature 23.0 °C, Time 86400 sec	1.2 % @Temperature 73.4 °F, Time 24.0 hour	ISO 62
Moisture Absorption at Equilibrium	0.40 % @Temperature 20.0 °C	0.40 % @Temperature 68.0 °F	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0050 cm/cm @Thickness 4.00 mm, Time 86400 sec	0.0050 in/in @Thickness 0.157 in, Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0080 cm/cm @Thickness 4.00 mm, Time 86400 sec	0.0080 in/in @Thickness 0.157 in, Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	27	27	Instantaneous, Conditioned 15 days at 23°C - 50% RH; ISO 868
	22 @Time 15.0 sec	22 @Time 0.00417 hour	Conditioned 15 days at 23°C - 50% RH; ISO 868
Tensile Strength at Break	32.0 MPa	4640 psi	Conditioned 15 days at 23°C - 50% RH; ASTM D638
Elongation at Break	>= 750 %	>= 750 %	Conditioned 15 days at 23°C - 50% RH; ASTM D638
Flexural Modulus	0.0120 GPa	1.74 ksi	Conditioned 15 days at 23°C - 50% RH; ISO178
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	ISO 179

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	@Temperature 23.0 °C	@Temperature 73.4 °F	ISO 179
	NB	NB	ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	134 °C	273 °F	ISO 11357
Vicat Softening Point	58.0 °C	136 °F	ISO 306
	@Load 1.02 kg	@Load 2.25 lb	

Processing Properties	Metric	English	Comments
Nozzle Temperature	210 °C	410 °F	Recommended
	180 - 240 °C	356 - 464 °F	
Mold Temperature	10.0 - 30.0 °C	50.0 - 86.0 °F	
Drying Temperature	55.0 - 65.0 °C	131 - 149 °F	
Dry Time	4.00 - 8.00 hour	4.00 - 8.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China