

Arlon 28561R015M 0.015" (0.381 mm) Uncured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction:Side 1: Uncured Silicone RubberSide 2: Uncured Silicone Rubber Appearance: Red silicone gum on fiberglass fabricThis data represents typical values for the production material. The data should not be used to write, or in place of, material specifications.Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-28561R015M-0015-0381-mm-Uncured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Thickness	>= 63.5 microns	>= 2.50 mil	Side 1
	>= 63.5 microns	>= 2.50 mil	Side 2
	76.2 microns	3.00 mil	Polyethylene Interleave Side 1
	127 microns	5.00 mil	Mylar on Side 2
	203 microns	8.00 mil	Prime Coated 1523 Fiberglass, Substrate
	356 - 406 microns	14.0 - 16.0 mil	Overall

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 50	40 - 50	Compound Property
Tensile Strength	>= 5.52 MPa	>= 800 psi	Compound Property
Elongation at Break	>= 500 %	>= 500 %	Compound Property
Peel Strength	>= 1.05 kN/m	>= 6.00 pli	Bond Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
	120 min	2.00 hour	

Cure Time Processing Properties	Metric @ Temperature 204 °C	English @ Temperature 400 °F	Recommended Postcure Cycle Comments
	15.0 min	0.250 hour	
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	Recommended Cure Cycle
Shelf Life	6.00 Month	6.00 Month	
	@Temperature 23.9 °C	@Temperature 75.0 °F	From date of manufacture

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	14.7 - 17.7	
Uncoated Fabric Break Strength	200 lb/in	Fill Direction, Substrate Property
	250 lb/in	Warp Direction, Substrate Property

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China