

Arlon 30560R015 0.015" (0.381 mm) Uncured/Unsupported Silicone Rubber on a Release Carrier

Category : Polymer , Thermoset , Silicone , Silicone Rubber

Material Notes:

Design/Construction:Side 1: Uncured/Unsupported Silicone Rubber on a Release Carrier Appearance: Red silicone gum on polymer linerThis data represents typical values for the production material. The data should not be used to write, or in place of, material specifications.Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-30560R015-0015-0381-mm-UncuredUnsupported-Silicone-Rubber-on-a-Release-Carrier.php

Physical Properties	Metric	English	Comments
Thickness	76.2 microns	3.00 mil	Polyethylene Interleave
	127 microns	5.00 mil	Kodacel Substrate
	356 - 406 microns	14.0 - 16.0 mil	Overall
	356 - 406 microns	14.0 - 16.0 mil	Side 1

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 50	40 - 50	Compound Property
Tensile Strength	>= 5.52 MPa	>= 800 psi	Compound Property
Elongation at Break	>= 500 %	>= 500 %	Compound Property

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	15.0 min	0.250 hour	Recommended Cure Cycle
	@Temperature 177 °C	@Temperature 350 °F	
	120 min	2.00 hour	Recommended Postcure Cycle
	@Temperature 204 °C	@Temperature 400 °F	

Shelf Life Processing Properties	6.00 Month Metric	6.00 Month English	From date of manufacture Comments
-------------------------------------	----------------------	-----------------------	--------------------------------------

Descriptive Properties	Value	Comments
------------------------	-------	----------

Color	Red	
-------	-----	--

Total Product Weight (oz/yd2)	14 - 16	
-------------------------------	---------	--

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China