

Arlon 51271R037 0.037" Uncured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Side 1: Uncured Silicone Rubber Substrate: Style 7628 Fiberglass Side 2: Uncured Silicone Rubber Interleave: 2.5 mil Polyethylene This data represents typical values for the production material and should not be used as material specifications. Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-51271R037-0037-Uncured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	203 microns	8.00 mil	Substrate; Arlon SQA-TMS-003
	229 microns	9.00 mil	Side 1; Arlon SQA-TMS-003
	508 microns	20.0 mil	Side 2; Arlon SQA-TMS-003
	940 microns	37.0 mil	Overall Thickness; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	Silicone Property; ASTM D2240
Tensile Strength	5.52 MPa	800 psi	Silicone Property; ASTM D412
Elongation at Break	225 %	225 %	Silicone Property; ASTM D412
Tear Strength	15.8 kN/m	90.0 pli	Silicone Property; ASTM D624
Peel Strength	1.51 kN/m	8.60 pli	Bond Strength (S1 to S2); Arlon SQA-TMS-011

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
UL RTI, Electrical	220 °C	428 °F	File E54153
UL RTI, Mechanical without Impact	220 °C	428 °F	File E54153

Electrical Properties	Metric	English	Comments
Dielectric Strength	27.2 kV/mm	690 kV/in	Arlon SQA-TMS-020

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Post Cure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 121 °C	@Pressure 50.0 psi, Temperature 250 °F	
Shelf Life	6.00 Month	6.00 Month	
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Red	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China