

Arlon 51579XA028 0.028" Uncured/Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Interleave: LDPE Layer 2: Uncured Silicone Rubber Layer 1: Cured Silicone Rubber Substrate: Style 7628 Fiberglass
This data represents typical values for the production material and should not be used as material specifications. Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-51579XA028-0028-UncuredCured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	102 microns	4.00 mil	Layer 1; Arlon SQA-TMS-003
	203 microns	8.00 mil	Substrate; Arlon SQA-TMS-003
	406 microns	16.0 mil	Layer 2; Arlon SQA-TMS-003
	711 microns	28.0 mil	Overall Thickness; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	44	44	Silicone Property; ASTM D2240
Tensile Strength	7.58 MPa	1100 psi	Silicone Property; ASTM D412
Elongation at Break	650 %	650 %	Silicone Property; ASTM D412
Peel Strength	4.38 kN/m	25.0 pli	Bond Strength (S1 to S1); Arlon SQA-TMS-011

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	17.7 kV/mm	450 kV/in	Arlon SQA-TMS-020

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Post Cure Cycle

Processing Properties	@Temperature 204 °C Metric	@Temperature 400 °F English	Comments
	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	
Shelf Life	6.00 Month	6.00 Month	
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Gray	
Total Product Weight (oz/yd2)	27.1	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China