

Arlon 55866R028 0.0295" Uncured/Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Interleave: 3 mil PESide 2: Uncured Silicone RubberSubstrate: Style 162 FiberglassSide 1: Cured Silicone Rubber
This data represents typical values for the production material and should not be used as material specifications. Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-55866R028-00295-UncuredCured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	102 microns	4.00 mil	Side 1; Arlon SQA-TMS-003
	165 microns	6.50 mil	Side 2; Arlon SQA-TMS-003
	483 microns	19.0 mil	Substrate; Arlon SQA-TMS-003
	749 microns	29.5 mil	Overall Thickness; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	Silicone Property; ASTM D2240
Tensile Strength	4.83 MPa	700 psi	Silicone Property; ASTM D412
Elongation at Break	200 %	200 %	Silicone Property; ASTM D412
Peel Strength	1.58 kN/m	9.00 pli	Bond Strength (S1 to S1); ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
UL RTI, Electrical	200 °C	392 °F	File E54153
UL RTI, Mechanical without Impact	200 °C	392 °F	File E54153

Electrical Properties	Metric	English	Comments
Dielectric Strength	19.7 kV/mm	500 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Post Cure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 121 °C	@Pressure 50.0 psi, Temperature 250 °F	
Shelf Life	6.00 Month	6.00 Month	
	@Temperature 23.9 °C	@Temperature 75.0 °F	

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	27.8	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China