

Arlon 55986C028 0.0295" Cured/Uncured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Interleave 1: N/A Side 1: Cured Silicone Rubber Substrate: Style 162 Fiberglass Side 2: Uncured Silicone Rubber Interleave 2: LDPET
This data represents typical values for the production material and should not be used as material specifications. Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-55986C028-00295-CuredUncured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.62 g/cc	0.0585 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	165 microns	6.50 mil	Side 1; Arlon SQA-TMS-003
	178 microns	7.00 mil	Side 2; Arlon SQA-TMS-003
	406 microns	16.0 mil	Substrate; Arlon SQA-TMS-003
	749 microns	29.5 mil	Overall Thickness; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	74	74	Silicone Property; ASTM D2240
Tensile Strength	5.78 MPa	838 psi	Silicone Property; ASTM D412
Elongation at Break	128 %	128 %	Silicone Property; ASTM D412
Tear Strength	15.6 kN/m	89.0 pli	Die B; Silicone Property; ASTM D624
Peel Strength	0.719 kN/m	4.10 pli	Bond Strength (S2 to S2); Arlon SQA-TMS-011

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability, UL94	V-0	V-0	designed to meet

Electrical Properties	Metric	English	Comments
Dielectric Strength	17.4 kV/mm	441 kV/in	Arlon SQA-TMS-020

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Post Cure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
	4.98 min	0.0830 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 121 °C	@Pressure 50.0 psi, Temperature 250 °F	
Shelf Life	6.00 Month	6.00 Month	
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Brown	
Total Product Weight (oz/yd2)	34.8	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China