

Arlon CP-PC-2951 Silicone Compound

Category : Polymer , Thermoset , Silicone , Silicone Rubber

Material Notes:

This data represents typical values for the production material and should not be used as material specifications. Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-CP-PC-2951-Silicone-Compound.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	Silicone Property; Arlon SQA-TMS-024

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	47	47	Silicone Property; ASTM D2240
Tensile Strength	5.17 MPa	750 psi	Silicone Property; ASTM D412
Elongation at Break	450 %	450 %	Silicone Property; ASTM D412

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Post Cure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	
Shelf Life	3.00 Month	3.00 Month	
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Red	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China