

Arlon UltraPad™ 55073R031 Silicone-Based Press Pad

Category : Polymer , Thermoset , Silicone , Silicone, Molded, Glass Fiber Filled

Material Notes:

UltraPad™ D65: Silicone Based Press PadDesign/Construction:Interleave: 3 mil PolyethyleneSide 1: Cured Silicone RubberSubstrate: Style 7628 FiberglassSide 2: Cured Silicone RubberThis data represents typical values for the production material and should not be used as material specifications.Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:
http://www.lookpolymers.com/polymer_Arlon-UltraPad-55073R031-Silicone-Based-Press-Pad.php

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in³	Silicone Property; Arlon SQA-TMS-024
Thickness	211 microns	8.30 mil	Substrate; Arlon SQA-TMS-003
	290 microns	11.4 mil	Side 1; Arlon SQA-TMS-003
	290 microns	11.4 mil	Side 2; Arlon SQA-TMS-003
	790 microns	31.1 mil	Overall Thickness; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	43	43	Silicone Property; ASTM D2240
	81	81	Product Property; ASTM D2240
Tensile Strength	7.79 MPa	1130 psi	Silicone Property; ASTM D412
Elongation at Break	854 %	854 %	Silicone Property; ASTM D412

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 - 300 °C	302 - 572 °F	Recommended Application Range
	@Pressure 0.000 - 5.00 MPa	@Pressure 0.000 - 725 psi	

Processing Properties	Metric	English	Comments
Shelf Life	60.0 Month	60.0 Month	
	@Temperature 22.8 °C	@Temperature 73.0 °F	

Descriptive Properties	Value	Comments
Color	Naturally White	Substrate

Descriptive Properties	Red Value	Product Comments
Service Life	114 hours	at 225°C and 2.07 MPa
Total Product Weight (oz/yd2)	26.2	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China