

Asahi Glass AFLAS® 150P TFE/P Fluoroelastomer

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

AFLAS® 100/150 fluoroelastomers are alternating copolymers of tetrafluoroethylene and propylene. They offer 1) excellent heat resistance, 2) exceptional chemical resistance especially to bases and amines, and 3) high electrical resistivity. AFLAS® 100/150 are categorized by ASTM D 1418-01 as class FEPM. Information provided by Asahi Glass Company, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Glass-AFLAS-150P-TFEP-Fluoroelastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.55 g/cc	1.55 g/cc	ASTM D792
Mooney Viscosity	95 @Temperature 100 °C	95 @Temperature 212 °F	ML1+10

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	72	72	
Tensile Strength at Break	17.7 MPa	2570 psi	ASTM D638
Elongation at Break	260 %	260 %	ASTM D638

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-3.00 °C	26.6 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	3.00e+16 ohm-cm	3.00e+16 ohm-cm	
Dielectric Strength	23.0 kV/mm	584 kV/in	ASTM D149

Descriptive Properties	Value	Comments
Fluorine Content %	57	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China