

Asahi Glass Fluon® PA1025Z 25% Glass Fiber, PTFE Filled Compound

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE , Polytetrafluoroethylene (PTFE), Glass Filled, Molded

Material Notes:

Fluon®PTFE FC has improved creep and wear resistance. A wide range of fillers such as glass fiber, graphite, bronze, carbon fiber are available. Information provided by Asahi Glass Company, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Glass-Fluon-PA1025Z-25-Glass-Fiber-PTFE-Filled-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.23 g/cc	2.23 g/cc	
Bulk Density	0.890 g/cc	0.0322 lb/in ³	
Particle Size	690 µm	690 µm	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	18.5 MPa	2680 psi	
Elongation at Break	290 %	290 %	

Descriptive Properties	Value	Comments
PTFE Content, %	75	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China