

Asahi Kasei Tenac®-C EF450 Copolymer Polyacetal Resin

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Applications: Automotive: Fuel Pump Module Parts Electrical and Industrial: Audio-Visual Equipment, Printer Equipment
Information provided by Asahi Kasei

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Tenac-C-EF450-Copolymer-Polyacetal-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.41 g/cc	1.41 g/cc	23°C
Melt Flow	3.7 g/10 min	3.7 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	48.0 MPa	6960 psi	
Charpy Impact, Notched	0.710 J/cm²	3.38 ft-lb/in²	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China