

Asahi Kasei Thermofil P-20TC-1156 20% Talc Filled, Heat Stabilized

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Talc Filler

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermofil-P-20TC-1156-20-Talc-Filled-Heat-Stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955
Melt Flow	15 g/10 min	15 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	95	95	ASTM D785
Tensile Strength, Yield	33.1 MPa	4800 psi	ASTM D638
Elongation at Yield	18 %	18 %	ASTM D638
Flexural Strength	51.7 MPa	7500 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	0.267 J/cm	0.500 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.27 J/cm	8.00 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear	59.4 $\mu\text{m/m-}^{\circ}\text{C}$	33.0 $\mu\text{in/in-}^{\circ}\text{F}$	ASTM D696
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	110 $^{\circ}\text{C}$	230 $^{\circ}\text{F}$	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	79.4 $^{\circ}\text{C}$	175 $^{\circ}\text{F}$	ASTM D648
Flame Spread	20 mm/min	0.80 in/min	Horizontal Burn Rate; FMVSS302

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China