

Asahi Kasei Thermofil P-40TC-1156 40% Talc Reinforced, Heat Stabilized

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermofil-P-40TC-1156-40-Talc-Reinforced-Heat-Stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	ASTM D955
Melt Flow	12 g/10 min	12 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	95	95	ASTM D785
Tensile Strength, Yield	29.6 MPa	4300 psi	ASTM D638
Elongation at Yield	10 %	10 %	ASTM D638
Flexural Strength	49.6 MPa	7200 psi	ASTM D790
Flexural Modulus	2.96 GPa	430 ksi	ASTM D790
Izod Impact, Notched	0.214 J/cm	0.400 ft-lb/in	ASTM D256
Izod Impact, Unnotched	2.14 J/cm	4.00 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	138 °C	280 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China