

Asahi Kasei Thermylene® P-20-0739 20% Talc Filled, High Impact, Heat Stabilized

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Talc Filler

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylene-P-20-0739-20-Talc-Filled-High-Impact-Heat-Stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	30.3 MPa	4400 psi	ASTM D638
Flexural Strength	42.7 MPa	6200 psi	ASTM D790
Flexural Modulus	1.93 GPa	280 ksi	ASTM D790
Izod Impact, Notched	0.908 J/cm	1.70 ft-lb/in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China