

Asahi Kasei Thermylene® P6-30FG-0600 30% Glass Fiber Reinforced, Heat Stabilized

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylene-P6-30FG-0600-30-Glass-Fiber-Reinforced-Heat-Stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	95	95	ASTM D785
Tensile Strength, Yield	82.7 MPa	12000 psi	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Flexural Strength	117 MPa	17000 psi	ASTM D790
Flexural Modulus	5.03 GPa	730 ksi	ASTM D790
Izod Impact, Notched	0.961 J/cm	1.80 ft-lb/in	ASTM D256
Izod Impact, Unnotched	5.34 J/cm	10.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear	37.8 µm/m-°C	21.0 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	162 °C	324 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	149 °C	300 °F	ASTM D648
Flame Spread	20 mm/min	0.80 in/min	Horizontal Burn Rate; FMVSS302

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China