

Asahi Kasei Thermylene® P7-40FG-0790 40% Glass Fiber Reinforced, Heat Stabilized

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Glass Fiber Filler

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylene-P7-40FG-0790-40-Glass-Fiber-Reinforced-Heat-Stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	ASTM D792
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	116	116	ASTM D785
Tensile Strength, Yield	110 MPa	16000 psi	ASTM D638
Elongation at Yield	2.0 %	2.0 %	ASTM D638
Tensile Modulus	10.3 GPa	1500 ksi	ASTM D638
Flexural Strength	152 MPa	22000 psi	ASTM D790
Flexural Modulus	7.31 GPa	1060 ksi	ASTM D790
Izod Impact, Notched	1.12 J/cm	2.10 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.94 J/cm	13.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear	25.2 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	14.0 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM D696
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	154 $^{\circ}\text{C}$	310 $^{\circ}\text{F}$	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China