

Asahi Kasei Thermylon® LSG-440A-H 60% Ceramic and Glass Fiber Reinforced, Heat

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylon-LSG-440A-H-60-Ceramic-and-Glass-Fiber-Reinforced-Heat.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.73 g/cc	1.73 g/cc	ASTM D792
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	193 MPa	28000 psi	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Flexural Strength	290 MPa	42000 psi	ASTM D790
Flexural Modulus	13.8 GPa	2000 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	ASTM D256
Izod Impact, Unnotched	8.54 J/cm	16.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	268 °C	515 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	252 °C	485 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China