

Asahi Kasei Thermylon® NSG-240A 50% Ceramic and Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylon-NSG-240A-50-Ceramic-and-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.58 g/cc	1.58 g/cc	ASTM D792
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	193 MPa	28000 psi	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Flexural Strength	290 MPa	42000 psi	ASTM D790
Flexural Modulus	12.4 GPa	1800 ksi	ASTM D790
Izod Impact, Notched	1.28 J/cm	2.40 ft-lb/in	ASTM D256
Izod Impact, Unnotched	11.2 J/cm	21.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear	41.4 $\mu\text{m/m-}^{\circ}\text{C}$	23.0 $\mu\text{in/in-}^{\circ}\text{F}$	ASTM D696
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	218 $^{\circ}\text{C}$	425 $^{\circ}\text{F}$	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	213 $^{\circ}\text{C}$	415 $^{\circ}\text{F}$	ASTM D648
Flammability, UL94	HB	HB	0.0591 in thickness

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China